

ALKYD RESIN SCCO 301X60

Viscosity	Gardner Bubble viscometers/25 ° c 60% solution in xylene : Z ₂ -Z ₄ /40-60 stock
Color Index	(%60 solution in xylene) Gardner color standard 1933:<4
Acid value	DIN 53183(mg koH/g of solid resin) 6-10
Density	20 ° c (g/ml) approx : 1.1-1.12
Solid %	%60 ± %1
Characteristics	Short Oil, non drying alkyd resin type of oil : soya bean form of supply : %60 solution in xylene
Properties	Excellent build and color retention with amino resins, very good adhesion and excellent gloss,good weather & yellowing resistance and compatibility with nitrocellulose.
Resin Composition (approx)	%30 OIL (Triglyceride) %43 phthalic anhydride

Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓	✓	✓



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,
Shahnazari Ave, Madar SQ, Tehran, Iran
Tel: +9821 2225 69 21 Fax:+9821 2225 91 71
Email:info@caspianro.com
Website: www.caspianro.com