

ALKYD RESIN SCLO 311X60

Viscosity	Gardner Bubble viscometers/25 ° c 60% solution in xylene : Z ₅ -Z ₇ /110-180 stock
Color Index	(%60 solution in white spirite) Gardner color standard 1933<8
Acid value	DIN 53183 mg koH/g of solid resin<14
Density	20 ° c (g/ml) approx : 1.09-1.11
Solid %	%60 ± %1
Characteristics	Short Oil, air drying alkyd resin Type of oil : tall oil Form of supply : %60 solution
Properties	Rapid and hard through drying, very good resistance to oils and water.
Resin Composition (approx)	%31 OIL (Triglyceride) %34 Phthalic anhydride

Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓	✓	limited



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,
Shahnazari Ave, Madar SQ, Tehran, Iran
Tel: +9821 2225 69 21 Fax: +9821 2225 91 71
Email: info@caspianro.com
Website: www.caspianro.com