

NITROCELLULOSE GLOSSY VARNISH

Product description

Nitrocellulose based wood varnish is developed for many usage over wood it is suitable for interior wood furniture, bamboo and high gloss and maximum hardness.

Technical information

1) Surface dry	10 min at 25 ° c
2) Hard dry	1-2 hr
3) Solid content	39±1
4) Sepecific gravity	0.96±0.05 gr/cm ³
5) Viscosity at 25 ° c	3623 c.p
6) Application method	Spray and brush
7) Cover rate	8-10 m ² /1kg
8) Interval coat	60 min

Surface preparations

Wipe with a clean tack cloth to remove any dust for extra protection, polish the surface.



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,
Shahnazari Ave, Madar SQ, Tehran, Iran
Tel: +9821 2225 69 21 Fax:+9821 2225 91 71
Email:info@caspiantro.com
Website: www.caspiantro.com