

## ALKYD RESIN MCSO 453W55

<b>Viscosity</b>	Gardner Bubble viscometers/25 ° c 55% solution in white spirit/xylene (80/20) : Z <sub>5</sub> -Z <sub>6</sub> /100-120 stock
<b>Color Index</b>	(%50 solution in white spirit/xylene) Gardner color standard 1933<6
<b>Acid value</b>	DIN 53183(mg koH/g of solid resin) 6-10
<b>Density</b>	20 ° c (g/ml) approx : 0.96-0.98
<b>Solid %</b>	%55 ± %1
<b>Characteristics</b>	Short Oil, none drying alkyd resin Type of oil : coconut oil Form of supply : %60 solution in xylene
<b>Properties</b>	Oxidizing alkyd resin, excellent color and gloss retention, medium viscosity, good drying hardness.
<b>Resin Composition (approx)</b>	%45 OIL (Triglyceride) %26 phthalic anhydride

### Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓		limited



**Caspian Ro Chemical Co.**

Head Office: Unit 12, No. 25, 2nd st,  
Shahnazari Ave, Madar SQ, Tehran, Iran  
Tel: +9821 2225 69 21 Fax: +9821 2225 91 71  
Email: info@caspiantro.com  
Website: www.caspiantro.com