

NITROCELLULOSE SOLUTION NC2000

Composition	%
Nitrocellulose E950 (damped 30% ethanol)	30
Buthyl acetate	25
Ethyl acetate	15
Aceton	5
Toluene	15
Xylene	10

Specifications	
Solid content ASTM D 1644	21 %
Viscosity at 20 ° c (2 part Butyl acetat-1 part NC2000 with cup 4)	80-100 sec
Density at 25 ° c ASTM D 1475	0.94±0.01 gr/cm ³
Colour (Gardner colour standard) 1933	MAX 3 gardner
Flash point ASTM D 93	<20 ° c

Physical properties

viscous, colour, less or pale yellow liquid

odour of the used solvents

used for N.C sanding sealer N.C putty & primer



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,

Shahnazari Ave, Madar SQ, Tehran, Iran

Tel: +9821 2225 69 21 Fax: +9821 2225 91 71

Email: info@caspianro.com

Website: www.caspianro.com