

## NITROCELLULOSE SOLUTION NC 2003-25

<b>Composition</b>	<b>%</b>
Nitrocellulose 560 alcoholic	30
Nitrocellulose 950 alcoholic	6
Buthyl acetate	40
Ethyl acetate	8
Methyl acetate	8
Toluene	8

<b>Specifications</b>	
Solid content ASTM D 1644	25%
Viscosity at 20 ° c with cup 4 (1 unit Lacquer + 2 unit butyl acetate )	90-100 sec
Density at 25 ° c ASTM D 1475	0.94±0.01 gr/cm <sup>3</sup>
Colour (Gardner colour standard) 1933	MAX 3 gardner
Flash point ASTM D 93	<20 ° c

### **Physical properties**

viscous, colour, less or pale yellow liquid

odour of the used solvents

Very good adhesion and flexibility, excellent gloss retention used for, wood coatings, automotive repair paints, industrial coatings, leather coatings.



### **Caspian Ro Chemical Co.**

Head Office: Unit 12, No. 25, 2nd st,  
Shahnazari Ave, Madar SQ, Tehran, Iran  
Tel: +9821 2225 69 21 Fax: +9821 2225 91 71  
Email: info@caspianro.com  
Website: www.caspianro.com