

## NITROCELLULOSE SOLUTION NC2005

<b>Composition</b>	<b>%</b>
Nitrocellulose E620 (damped 30% Ethanol)	40
Buthyl acetate	30
Ethyl acetate	5
Aceton	5
Toluene	10
Xylene	10

<b>Specifications</b>	
Solid content ASTM D 1644	28 %
Viscosity at 20 ° c (2 part Butyl acetat-1 part NC2005 with cup 4)	100-120 sec
Density at 25 ° c ASTM D 1475	0.94±0.01 gr/cm <sup>3</sup>
Colour (Gardner colour standard) 1933	MAX 3 gardner
Flash point ASTM D 93	<20 ° c

### **Physical properties**

viscous, colour, less or pale yellow liquid

odour of the used solvents

Very good adhesion and flexibility, excellent glass retention used fo, wood coatings automotive repair paints industrial coating, leather coatings.



#### **Caspian Ro Chemical Co.**

Head Office: Unit 12, No. 25, 2nd st,  
Shahnazari Ave, Madar SQ, Tehran, Iran  
Tel: +9821 2225 69 21 Fax: +9821 2225 91 71  
Email: info@caspianro.com  
Website: www.caspianro.com