

NITROCELLULOSE SOLUTION NC730

Composition	%
Nitrocellulose E560 (Alcoholic 30% damp)	43
Buthyl acetate	30
Ethyl acetate	7
Aceton	7
Toluene	10
Buthyl glycol	3

Specifications	
Solid content ASTM D 1644	30 %
Viscosity at 20 ° c (2 part Butyl acetat-1 part NC730 with cup 4)	70-80sec
Density at 25 ° c ASTM D 1475	0.94±0.01 gr/cm ³
Colour (Gardner colour standard) 1933	MAX 3 gardner
Flash point ASTM D 93	<20 ° c

Physical properties

viscous, colour, less or pale yellow liquid

odour of the used solvents

Very good adhesion and flexibility, excellent gloss retention used for, wood coatings, automotive repair paints, industrial coatings, leather coatings.



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,
Shahnazari Ave, Madar SQ, Tehran, Iran
Tel: +9821 2225 69 21 Fax: +9821 2225 91 71
Email: info@caspianro.com
Website: www.caspianro.com