

NITROCELLULOSE SOLUTION NC A400-28

Composition	%
Nitrocellulose Alcoholic (30% ethanol damp)	40
Ethyl acetate	20
Ethanol	40

Specifications	
Solid content ASTM D 1644	28%
Viscosity at 25 ° c	110±10 ku
Density at 25 ° c ASTM D 1475	0.94±0.01 gr/cm ³
Colour (Gardner colour standard) 1933	MAX 3 gardner
Flash point ASTM D 93	<20 ° c

Physical properties

Pale yellow liquid

Odour of the used solvents

Used for printing inks, for instance for printing plastic films and aluminum foils intended mainly for food packaging. the printing methods involved are rotogravure and flexography printing.



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,
Shahnazari Ave, Madar SQ, Tehran, Iran
Tel: +9821 2225 69 21 Fax: +9821 2225 91 71
Email: info@caspianro.com
Website: www.caspianro.com