

NC ALCOHOLEATED SEPCIFICATION A30(A400)

TESTS	SPESECIFICATION
Nitrogen Content (%)	10.7 - 11.2
Viscosity (DIN 53179)	400±25CPS
B&J Stability Test in 132 ± 0.2 ° C (ml/gr)	MAX 1.5
Moisture(%)	MAX 4
Damping Medium (Ethanol)	30 ± 2 %
Acidity % (as H2SO4) Dry NC	MAX 0.065

Measuring viscosity according DIN 53179:

Measuring instrument: Hoeppler viscometer precisin model,ball4 with viscosity solution (see I)

!For preparation viscosity solution mixing 30% by weight dry solid without plastizier NC A30(A400) with 70% by weight solvent.

(solvent:95% by weight Acetone +5% by weight water)

Measuring temperature: 25°c

Standard range for viscosity according DIN53179:400cps ± 25cps

Main Applications :

Pilishes, polishing lacquers,printing inks,paper lacquers.



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,

Shahnazari Ave, Madar SQ, Tehran, Iran

Tel: +9821 2225 69 21 Fax:+9821 2225 91 71

Email:info@caspiantro.com

Website: www.caspiantro.com