

## ALKYD RESIN MCSO 463W50

<b>Viscosity</b>	Gardner Bubble viscometers/25 ° c 50% solution in white spirit/xylene (80/20) : Z <sub>5</sub> -Z <sub>6</sub> /80-160 stock
<b>Color Index</b>	(%50 solution in white spirit/xylene) Gardner color standard 1933<6
<b>Acid value</b>	DIN 53183(mg koH/g of solid resin) : 6-10
<b>Density</b>	20 ° c (g/ml) approx : 0.95-0.97
<b>Solid %</b>	%50 ± %1
<b>Characteristics</b>	Medium Oil, air drying alkyd resin Type of oil : soya bean Form of supply : %55 solution in white spirit/xylene
<b>Properties</b>	Oxidizing alkyd resin with high viscosity, Good resistance to weather,excellent color and gloss retention, good resistance against yellowing, high hardness and fast drying.
<b>Resin Composition (approx)</b>	%46 OIL (Triglyceride) %34 phthalic anhydride

### Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓	✓	limited



**Caspian Ro Chemical Co.**

Head Office: Unit 12, No. 25, 2nd st,  
Shahnazari Ave, Madar SQ, Tehran, Iran  
Tel: +9821 2225 69 21 Fax:+9821 2225 91 71  
Email:info@caspiantro.com  
Website: www.caspiantro.com