

NITROCELLULOSE SANDING SEALER

Product description

It is a nitrocellulose base air-drying sealer developed specially for wooden product before topcoating and easy sanding and excellent filling.

Technical information

1) Surface dry	5-10 min at 25 ° c
2) Hard dry	1-2 hr
3) Solid content	40±1
4) Specific gravity	1.003±0.05
5) Viscosity at 25 ° c	3811 c.p
6) Application method	Spray
7) Cover rate	8-10 m ² /1kg
8) Interval coat	60 min

Surface preparations

- 1) Surface should be clean and free of dust, grease and oil.
- 2) Surface should be sanded using grit sand paper number 120



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,
Shahnazari Ave, Madar SQ, Tehran, Iran
Tel: +9821 2225 69 21 Fax:+9821 2225 91 71
Email: info@caspianro.com
Website: www.caspianro.com